



River Rock



Dijon



Dahlia



Plum



Venetian



Infinity



India Ink



Sprout



Geranium

Construction	Values	Test Method
Surface Composition	Polyurethane	
Backing Composition	100% Rayon	ASTM D 751-06
Finished Width	54" Width	ASTM D 751-06
Put-up	30 yards	
Repeat	None	
Cleaning Code	W	
Railroaded	No	

Performance	Minimum Values	Test Method
Grab Tensile	60 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	10% × 15%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - PASS	TM582
Wyzenbeek Abrasion	Pass - 100,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ISO 1419: 1995
UV Stability	150 hours	ASTM D 4329-05
Crock Resistance	Wet-4; Dry-4	AATCC 8-2007
Cold Crack (#5 roller)	-20°F	CFFA-6A

Flammability	Environmental	
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
NFPA 260	Pass	2. Does not contain PFAS, PFOA
U.F.A.C. Class I	Pass	3. Prop 65 compliant
		4. No chemical flame retardants, CA AB2998 compliant
		5. REACH, RoHS, and LEED compliant

Suitable Applications Hospitality, Contract, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

