



ILLUSION




White



Stone



Buckskin



Mushroom




Topaz



Brown



Black



Charcoal

Technical Specifications

Technical Specifications	Values	Test Method
Top Finish	Polyurethane	ASTM D 751-06
Surface Composition	PVC Foam	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

Performance	Values	Test Method
Grab Tensile	80 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18 lbs./in. min.	ASTM D 751-06
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13
UV Stability	150 hours (no color change)	ASTM D 4329-05
Hydrolysis Resistance	5 weeks	ISO 1419: 1995

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass
FMVSS/CMVSS #302	Pass

Environmental

Does not contain any flame retardant chemicals.

Suitable Applications

Hospitality, Contract

Cleaning

Remove ordinary dirt and smudges with mild soap and water. Do not use chemical cleaners or disinfectants.