









Construction	Values	Test Method	
Surface Composition	100% Polyurethane		
Backing Composition	100% Polyester	ASTM D 751-06	
Finished Width	54" min.	ASTM D 751-06	
Repeat	None		
Railroaded	No		
Put-up	30 yards		
Cleaning Code	W/S		
Performance	Values	Test Method	
Grab Tensile	80 lbs./in.× 80 lbs./in.	ASTM D 751-06	
Trap Tear	15 lbs./in. × 15 lbs./in.	ASTM D 751-06	
Seam Strength	40 lbs./in. × 40 lbs./in.	ASTM D 751-06	
Adhesion	4 lbs./in. × 4 lbs./in	ASTM D 751-06	
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%	ASTM D 751-06	
Flex Resistance	25,000 cycles	ASTM D 2097-91	
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872	
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007	
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	ASTM D 4157-07	
Hydrolysis Resistance	10 weeks	ASTM D 3690-02	
	10 weeks	ISO 1419: 1995	
Colorfastness to Light	200 hours	ASTM D 4329-05	
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03	
Cold Crack (#5 roller)	-20°F	CFFA-6A	

California Technical Bulletin 117-2013, Sec. 1 Pass IMO A.652(16)8.2 Pass NFPA 260 Pass U.F.A.C. Class I Pass

Environmental

- 1. No anti-microbial additives
- 2. Does not contain PFAS, PFOA
- 3. Prop 65 compliant
- 4. No chemical flame retardants, CA AB2998 compliant
- 5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



