



Beige



Jesse James



Wild Bunch



Pecan



Dalton Gang



Coffee



Black



Graphite

Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	40 yards	
Cleaning Code	W	

Performance	Minimum Values	Test Method
Grab Tensile	150 lbs./in. × 100 lbs./in. min.	ASTM D 5034-09
Trap Tear	20 lbs./in. × 20 lbs./in. min.	ASTM D 5587-07
Seam Strength	70 lbs./in. × 60 lbs./in. min.	ASTM D 1683-11A
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-89
Stretch @ 15# (MD×CD)	2% × 9%	ASTM D 751-89
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Crock Resistance	Wet-4; Dry-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13
Hydrolysis Resistance	3 weeks	ISO 1419-1995 E
UV Stability	40 hours	AATCC 16-2004

Flammability	Environmental	
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
NFPA 260	Pass	2. Does not contain PFAS, PFOA
U.F.A.C. Class I	Pass	3. Prop 65 compliant
		4. No chemical flame retardants, CA AB2998 compliant
		5. REACH, RoHS, and LEED compliant

Suitable Applications Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel.

