









Construction	Values	Test Method			
Surface Composition	100% Polyurethane				
Backing Composition	100% Polyester	ASTM D 751-89			
Finished Width	54" min.	ASTM D 751-89			
Repeat	None				
Railroaded	No				
Put-up	30 yards				
Cleaning Code	W/S				
Performance	Minimum Values	Test Method			
Grab Tensile	95 lbs./in.× 80 lbs./in. min.	ASTM D 5035-09			
Trap Tear	15 lbs./in. × 15 lbs./in. min.	/in. min. ASTM D 5587-07			
Seam Strength	40 lbs./in. × 35 lbs./in. min. ASTM D 1683-07A				
Adhesion	4 lbs./in. × 4 lbs./in. min. ASTM D 751-89				
Stretch @ 15# (MD×CD)	2% × 12%	5 × 12% ASTM D 751-89			
Flex Resistance	25,000 Cycles	ASTM D 2097-91			
Blocking	No. 1 - Pass	Federal Standard 191A, 5304			
Crock Resistance	Dry-4; Wet-4	Federal Standard 191A, 5651			
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	000 cycles, #10 Cotton Duck ASTM D 4157-07			
Hydrolysis Resistance	7 weeks ASTM D3690-02				
UV Stability	1000 hours AATCC 16-2004				
Blue Dye Transfer Resistance	Dry 4-5; Wet 4-5 LP-463KC-04-03				

-					
ы		nm		hil	141/
	uп		u	ווע	шу

Cold Crack

California Technical Bulletin 117-2013, Sec. 1 Pass IMO A.652(16)8.2 Pass NFPA 260 Pass U.F.A.C. Class I Pass

Environmental

- 1. No anti-microbial additives
- 2. Does not contain PFAS, PFOA
- 3. Prop 65 compliant
- 4. No chemical flame retardants, CA AB2998 compliant

CFFA-6A

5. REACH, RoHS, and LEED compliant

<u>Suitable Applications</u> Contract, Healthcare, Hospitality, Residential

-20°F

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



